



# KUMHO PETROCHEMICAL

Kumho Chemical Laboratory, #1577 Yuseong-daero, Yuseong-gu, Daejeon, 305-348, Korea

[polymer@kkpc.com](mailto:polymer@kkpc.com), [ykhwang12@kkpc.com](mailto:ykhwang12@kkpc.com)

(TEL: 82-42-865-8685/8798, FAX:82-42-865-8797)

## Typical Property

Product: STE1055D

Color: NT

Property	Method (ASTM)	Unit	Result
Hardness	ASTM D-2240	Shore-D	55±2
Tensile Strength	ASTM D-638	kgf/cm <sup>2</sup>	120 이상
Elongation at Break	ASTM D-638	%	80 이상
Density	ASTM D-792	g/cm <sup>3</sup>	1±0.02
Melt Flow Index (200 °C, 5kg)	ASTM D-1238	g/10min	18±2