



KUMHO PETROCHEMICAL

Kumho Chemical Laboratory, #1577 Yuseong-daero, Yuseong-gu, Daejeon, 305-348, Korea

polymer@kkpc.com, ykhwang12@kkpc.com

(TEL: 82-42-865-8685/8798, FAX:82-42-865-8797)

Mill Sheet

Grade: STE1092LP(heel counter)

Color: NT

PROPERTIES	TEST METHOD	UNIT	VALUE
HARDNESS	ASTM D 2240	Shore A	92
TENSILE STRENGTH	ASTM D 638	kgf/cm ²	95
ELONGATION AT BREAK	ASTM D 638	%	500
DENSITY	ASTM D 792	g/cm ³	1.12
MELT FLOW INDEX (190°C, 5kg)	ASTM D 1238	g/10 min.	15