

Technical Data Sheet (ISO)

ABS(Acrylonitrile Butadiene Styrene)

ABS 720

Features	High rigidity
Applications	Cassettes, Radios, Video tape cases

Physical	Test Method	Value
Specific gravity	ISO 1183	1.04
Melt Flow Index (220°C, 10kg)	ISO 1133	20 g/10min
Water absorption	ISO 62	- %
Mold Shrinkage	ISO 294-4	0.5 ~ 0.8 %

Mechanical	Test Method	Value
Tensile Strength(at yield)	ISO 527	47 Mpa
Elongation(at break)	ISO 527	22 %
Flexural Strength	ISO 178	71 MPa
Flexural Modulus	ISO 178	2,450 Mpa
Izod Impact Strength(23°C)	ISO 180/1A	21 KJ/m ²
Charpy Impact Strength(23°C)	ISO 179/1eA	22 KJ/m ²
Rockwell Hardness(R scale)	ISO 2039-2	112

Thermal	Test Method	Value
Heat Deflection Temperature(1.8Mpa, Unannealed)	ISO 75-2	82 °C
Heat Deflection Temperature(0.45Mpa, Unannealed)	ISO 75-2	93 °C
Vicat Softening Temperature(B50)	ISO 306	97 °C

Flammability	Test Method	Value
Flame Rating - UL (1.6mm)	UL 94	HB

Notes

These are just typical properties, not specifications. Users should confirm results by their own test.