

## Technical Data Sheet

### SAN(Styrene Acrylonitrile)

### SAN 350F

<b>Features</b>	High strength
<b>Applications</b>	ABS Compounding, Electric & electronic parts

Physical	Test Method	Value
Density	ASTM D792	1.07 g/cm <sup>3</sup>
Melt Flow Index	(230°C, 3.8kg)	28.0 g/10min
	(200°C, 5.0kg)	7.3 g/10min
Mold Shrinkage	ASTM D955	0.2 ~ 0.6 %
Water absorption	ASTM D570	0.3 %

Mechanical	Test Method	Value
Tensile Strength	ASTM D638	680 kg/cm <sup>2</sup> (9,656) (psi)
Elongation	ASTM D638	4.5 %
Flexural Strength	ASTM D790	810 kg/cm <sup>2</sup> (11,500) (psi)
Flexural Modulus	ASTM D790	35,500 kg/cm <sup>2</sup> (504,100) (psi)
Izod Impact Strength(3.2mm)	ASTM D256	1.5 kgcm/cm (0.28) (ft-lb/in)
Rockwell Hardness(M scale)	ASTM D785	86

Thermal	Test Method	Value
Heat Deflection Temperature(18.6kgf/cm <sup>2</sup> )	ASTM D648	91 °C (196) (°F)
Vicat Softening Temperature(1kg, 50°C/h)	ASTM D1525	107 °C (225) (°F)

Flammability	Test Method	Value
Flame Rating - UL (1.6mm)	UL 94	HB

#### Notes

These are just typical properties, not specifications. Users should confirm results by their own test.

## Technical Data Sheet

### SAN(Styrene Acrylonitrile)

### SAN 350F

#### Processing guide

Injection Guide	Unit	Value
Nozzle	°C	190~220
Front	°C	190~210
Middle	°C	180~200
Rear	°C	170~190
Hopper Throat	°C	45
Mold	°C	40~70

Drying	Unit	Value
Temperature	°C	75~85
Time	hr	2~4

#### Notes

These are only mentioned as general guidelines.